

PVC

K-70

Producer

Ghadir Petrochemical Company

Properties	Value	Units
K- Valve	70±1	...
Inherent Viscosity	0.98~1.04	...
Fish eye	0~25	No.
Dark resin (Particle in 250 g PVC)	30	Max No.
Retained on mesh 40	Trace	Min.Wt%
Retained on mesh 63	90	Max.Wt%
Retained on mesh 250	5	Max.Wt%
Bulk Density	445~505	g/l
Flow Time	15~20	Sec.
Plasticiser Acptance (g DOP / 100 g PVC)	25~35	DOP/100g
Residual VCM Content	1	Max.ppm
Volotiles (Heat Loss)	0.3	Max.Wt%