



POLYMERAN GROUP

Injection Grades

I3

Application

Injection moulding /crates / Engineering parts/ closures

Producer

Marun Petrochemical Company

Density(iso 1183)	MFI(iso 1133) (190°-5 kg)	MFI Iso 1133 (190°-2.16 kg)
0.957	23	8