

1600JX₁

Application

Skirt of PET bottle

Characteristic

Different in stabilizer from 1600J

Producer

Mehr Petrochemical Company

Injection Molding Grade

Properties	Value	Units
Melt Index (190 ⁰ c/2.16kg)	18	g/10 min
Density	0.955	Kg/cm ³
MWD	Narrow	