



POLYMERAN GROUP

## 2200J X<sub>1</sub>

### Application

Caps

### Characteristic

Different in stabilizer from 2200J

### Producer

Mehr Petrochemical Company

### Injection Molding Grade

Properties	Value	Units
Melt Index (190 <sup>0</sup> c/2.16kg)	5.2	g/10 min
Density	0.964	Kg/cm <sup>3</sup>
MWD	Narrow	