

5300B

Application

Kerosene containers , Chemical containers, automobile oil containers, large toys floats.

Characteristic

Excellent rigidity and impact strength, large containers and industrial uses

Producer

Mehr Petrochemical Company

Blow Molding Grades

Properties	Value	Units
Melt Index (190 ⁰ c/2.16kg)	0.32	g/10 min
Density	0.960	Kg/cm ³
MWD	Medium	