

## Polyester Partially Oriented Yarn PET-HT105 (High Tenacity Yarn)

**Producer**

Tonggoyan Petrochemical Company

Properties	Units	Value
Intrinsic Viscosity	dl/g	1.00 ± 0.02
Color (CIE Lab)	*L	84≥
	*b	2≤
Carboxyl End Group	meq/kg	27≤
Melting point	°C	258≥
Water content	%wt	≤ 0.5
Chip Weight	g/100EA	1.7±0.1